

## Etronit MBM - Sheet

<b>Components:</b>	Paper - Phenol/Melamine
<b>Colour*:</b>	● Grey
<b>Serial no.:</b>	110
<b>Version no.:</b>	V1.0-17/06/15

### Closest relevant standards

<b>IEC 60893:</b>	-
<b>DIN 7735:</b>	-
<b>NEMA LJ 1:</b>	-

Mechanical properties	Test method	Thickness	Value	Unit	
Bending strength at RT	ISO 178	≥ 1,5 mm	120	MPa	*1
Bending strength at a high temperature	ISO 178	≥ 1,5 mm	-	MPa	-
Modulus of elasticity	ISO 178	≥ 1,5 mm	10000	MPa	*1
Compressive strength	ISO 604	≥ 5 mm	300	MPa	*1
Izod impact strength, parallel with layers	ISO 180/2A	≥ 5 mm	3.3	Kj/m <sup>2</sup>	*1
Shearing strength, parallel	ISO 60893-2	≥ 5 mm	35	MPa	*1
Tensile strength	ISO 527	≥ 1,6 mm	90	MPa	*1

Electrical properties	Test method	Thickness	Value	Unit	
Electrical strength in oil at 90°C, perpendicular	IEC 60243-1	3 mm	5	kV/mm	*2
Electrical strength in oil at 90°C, parallel	IEC 60243-1	≥ 3 mm	15	kV/25mm	*2
Permittivity 50 MHz	IEC 62631-2-1	≤ 3 mm	6		*3
Permittivity 1 MHz	IEC 62631-2-1	≤ 3 mm	-		-
Dissipation factor 50 MHz	IEC 62631-2-1	≤ 3 mm	0.04		*3
Dissipation factor 1 MHz	IEC 62631-2-1	≤ 3 mm	-		-
Insulation resistance after submersion in water	IEC 62631-3-3	All	100	MΩ	*4
Comparative tracking index	IEC 60112	≥ 3 mm	500	CTI	*1

### Conditioning

- 1 24h/23°C/50%RH
- 2 24h/23°C/50%RH + 1h/ in oil at 90°C
- 3 96h/105°C + 1h/23°C/20%RH
- 4 24h/50°C/<20% RH + 24h in water at 23°C
- 5 96h/105°C + 1h/ in oil at 90°C

### Notes

- A 1h/130°C / measured at 130°C
- B 1h/150°C / measured at 150°C
- C Halogen free
- D 1h/180°C / measured at 180°C
- E 1h/200°C / measured at 200°C

The above values are average values resulting from extensive tests in our laboratories. ELEKTRO-ISOLA A/S disclaims any and all liability for the performance of our materials in applications outside our control. Elektro-Isola A/S reserves the right to modify the above data without notice or further information. Furthermore, we refer to our general disclaimer.

\* Note that color and surface are indicative. As this is a technical product, colour and expression may vary according to dimensions, batches and machining. If you want further information or have special decorative needs, please feel free to contact us.

## Etronit MBM - Sheet

<b>Components:</b>	Paper - Phenol/Melamine
<b>Colour:</b>	● Grey
<b>Serial no.:</b>	110
<b>Version no.:</b>	V1.0-17/06/15

### Closest relevant standards

<b>IEC 60893:</b>	-
<b>DIN 7735:</b>	-
<b>NEMA LJ 1:</b>	-

Physical and thermal properties	Test method	Thickness	Value	Unit	
Temperature index 20,000 h (T.I.)	IEC 60216	≥ 3 mm	120	°C	-
Fire class	IEC 60695-11-10	≥ 8 mm	V-0	-	-
Density	ISO 1183-A	All	1.4	g/cm <sup>3</sup>	-
Water absorption	ISO 62-1	50x50x3 mm	100	mg	-
Smoke emission & toxicity	EN 45545-2; R22, R23 & R24	-	-	-	-
Oxygen Index (OI)	EN ISO 4589-2	-	-	%	-
Smoke density (Ds max.)	EN ISO 5659-2	-	-	-	-
Smoke density (Ds max.)	EN ISO 5659-2	-	-	-	-
Toxicity (CIT <sub>NLP</sub> )	NF X70-100-1/-2	-	-	-	-

### Characteristics and applications

Same surface properties as Etronit 201 MBM, but the basic material is identical to Etronit IIQ, i.e. it has sufficiently good electrical properties for insulation in low-voltage constructions. Self-extinguishing surface at thicknesses above 8 mm. Rail supports at electrical switchboard systems. Cabinet-installed systems, dividing plates, rear and installation panels.

### Conditioning

1	24h/23°C/50%RH
2	24h/23°C/50%RH + 1h/ in oil at 90°C
3	96h/105°C + 1h/23°C/20%RH
4	24h/50°C/<20% RH + 24h in water at 23°C
5	96h/105°C + 1h/ in oil at 90°C

### Notes

A	1h/130°C / measured at 130°C
B	1h/150°C / measured at 150°C
C	Halogen free
D	1h/180°C / measured at 180°C
E	1h/200°C / measured at 200°C

The above values are average values resulting from extensive tests in our laboratories. ELEKTRO-ISOLA A/S disclaims any and all liability for the performance of our materials in applications outside our control. Elektro-Isola A/S reserves the right to modify the above data without notice or further information. Furthermore, we refer to our general disclaimer.

\* Note that color and surface are indicative. As this is a technical product, colour and expression may vary according to dimensions, batches and machining. If you want further information or have special decorative needs, please feel free to contact us.