

Etronit MBM - Sheet

Components:	Paper - Phenol/Melamine
Colour*:	● Grey
Serial no.:	110
Version no.:	V1.0-17/06/15

Closest relevant standards

IEC 60893:	-
DIN 7735:	-
NEMA LJ 1:	-

Mechanical properties	Test method	Thickness	Value	Unit	
Bending strength at RT	ISO 178	≥ 1,5 mm	120	MPa	*1
Bending strength at a high temperature	ISO 178	≥ 1,5 mm	-	MPa	-
Modulus of elasticity	ISO 178	≥ 1,5 mm	10000	MPa	*1
Compressive strength	ISO 604	≥ 5 mm	300	MPa	*1
Izod impact strength, parallel with layers	ISO 180/2A	≥ 5 mm	3.3	Kj/m ²	*1
Shearing strength, parallel	ISO 60893-2	≥ 5 mm	35	MPa	*1
Tensile strength	ISO 527	≥ 1,6 mm	90	MPa	*1

Electrical properties	Test method	Thickness	Value	Unit	
Electrical strength in oil at 90°C, perpendicular	IEC 60243-1	3 mm	5	kV/mm	*2
Electrical strength in oil at 90°C, parallel	IEC 60243-1	≥ 3 mm	15	kV/25mm	*2
Permittivity 50 MHz	IEC 62631-2-1	≤ 3 mm	6		*3
Permittivity 1 MHz	IEC 62631-2-1	≤ 3 mm	-		-
Dissipation factor 50 MHz	IEC 62631-2-1	≤ 3 mm	0.04		*3
Dissipation factor 1 MHz	IEC 62631-2-1	≤ 3 mm	-		-
Insulation resistance after submersion in water	IEC 62631-3-3	All	100	MΩ	*4
Comparative tracking index	IEC 60112	≥ 3 mm	500	CTI	*1

Conditioning

- 1 24h/23°C/50%RH
- 2 24h/23°C/50%RH + 1h/ in oil at 90°C
- 3 96h/105°C + 1h/23°C/20%RH
- 4 24h/50°C/<20% RH + 24h in water at 23°C
- 5 96h/105°C + 1h/ in oil at 90°C

Notes

- A 1h/130°C / measured at 130°C
- B 1h/150°C / measured at 150°C
- C Halogen free
- D 1h/180°C / measured at 180°C
- E 1h/200°C / measured at 200°C

The above values are average values resulting from extensive tests in our laboratories. ELEKTRO-ISOLA A/S disclaims any and all liability for the performance of our materials in applications outside our control. Elektro-Isola A/S reserves the right to modify the above data without notice or further information. Furthermore, we refer to our general disclaimer.

* Note that color and surface are indicative. As this is a technical product, colour and expression may vary according to dimensions, batches and machining. If you want further information or have special decorative needs, please feel free to contact us.

Etronit MBM - Sheet

Components:	Paper - Phenol/Melamine
Colour:	● Grey
Serial no.:	110
Version no.:	V1.0-17/06/15

Closest relevant standards

IEC 60893:	-
DIN 7735:	-
NEMA LI 1:	-

Physical and thermal properties	Test method	Thickness	Value	Unit	
Temperature index 20,000 h (T.I.)	IEC 60216	≥ 3 mm	120	°C	-
Fire class	≥ 8 mm	≥ 8 mm	V-0	-	-
Density	ISO 1183-A	All	1.4	g/cm ³	-
Water absorption	ISO 62-1	50x50x3 mm	100	mg	-
Smoke emission & toxicity	-	-	-	-	-
Oxygen Index (OI)	EN ISO 4589-2	-	-	-	-
Smoke density (Ds max)	-	-	-	-	-
Smoke density (Ds max)	-	-	-	-	-
Toxicity (CIT _{NLP})	NF X70-100-1/-2	-	-	-	-
Toxicity (CIT _{G, 8 min})	EN 17084	-	-	-	-

Characteristics and applications

Same surface properties as Etronit 201 MBM, but the basic material is identical to Etronit IIQ, i.e. it has sufficiently good electrical properties for insulation in low-voltage constructions. Self-extinguishing surface at thicknesses above 8 mm. Rail supports at electrical switchboard systems. Cabinet-installed systems, dividing plates, rear and installation panels.

Conditioning

1	24h/23°C/50%RH
2	24h/23°C/50%RH + 1h/ in oil at 90°C
3	96h/105°C + 1h/23°C/20%RH
4	24h/50°C/<20% RH + 24h in water at 23°C
5	96h/105°C + 1h/ in oil at 90°C

Notes

A	1h/130°C / measured at 130°C
B	1h/150°C / measured at 150°C
C	Halogen free
D	1h/180°C / measured at 180°C
E	1h/200°C / measured at 200°C

The above values are average values resulting from extensive tests in our laboratories. ELEKTRO-ISOLA A/S disclaims any and all liability for the performance of our materials in applications outside our control. Elektro-Isola A/S reserves the right to modify the above data without notice or further information. Furthermore, we refer to our general disclaimer.

* Note that color and surface are indicative. As this is a technical product, colour and expression may vary according to dimensions, batches and machining. If you want further information or have special decorative needs, please feel free to contact us.